

TECHNICAL DATA SHEET



RAKAM



102 RAK TILE FIX HB

Hi-Build Tile Adhesive

RAK TILE FIX-HB is a polymer modified cementitious tile adhesive. It is supplied as grey or white coloured powder. It is water resistant and does not contain fiber, asbestos & other harmful components.

ADVANTAGES

- Enhanced bond and tensile strengths
- Water resistance
- Eco-friendly
- Good open time and slip resistance
- Formulated to suit Middle East conditions

USES

RAK TILE FIX-HB is used for fixing of ceramic tiles in interior and exterior applications especially to those exposed to permanently wet condition.

It may be suitable for use in :

- Institutional Kitchen
- Bathrooms
- Shower rooms
- Swimming pools
- Laboratories
- Hospitals
- Ceramic, vitrified tiles, granite floors

TECHNICAL PROPERTIES

Properties

Properties	Result
Appearance	Powder
Color	Grey or White
Dry Density	1.55 kg/L
Wet Density	1.70 kg/L
VOC	2.7 g/L
Water resistance	excellent
Slip resistance	excellent
Open Time	Approx. 20 minutes
Workable Time	45 minutes
Wall Grouting	After 10 hours
Floor Grouting	After 24 hours
Shear Strength	1.6 N/mm ²
(ANSI 118.4-1992)	
Adhesion Strength	
(EN 1348)	
Initial adhesion at 28days	1.5 N/mm ²
Adhesion after heat	0.95 N/mm ²
Adhesion after water immersion	1.1 N/mm ²
Adhesion after Freeze thaw cycle	1.00 N/mm ²
All values are subject to 5-10 % tolerance	

INSTRUCTIONS FOR USE

Surface Preparation

All surfaces should be sound, clean & uncontaminated. This preparation should leave an exposed concrete surface free from dust, loose particles, deleterious matter, oil, grease, chemical films & other contaminant.

All loose particles of mortar, paint, etc. must be physically removed.

Concrete or blockwork: should be allowed to cure sufficiently so that all shrinkage movements take place before fixing tiles.

Gypsum supports: must be treated with BONDING AGENT. Should not have a percentage of humidity more than 10%.

The surface of substrates must be moistened slightly with clean water to reduce the absorption of water from the mortar. Do not moistened the tiles.

Place the tiles onto the adhesive bed. Apply sufficient pressure on the tile during fixing it with slight twisting movement in order to ensure good contact with the adhesive.

In case of large size tiles, it is necessary to spread the adhesive also to the backside of the tile and then place the tiles into the adhesive bed.

Apply enough material that can be tiled during the adhesive's open wet time. Spreading large areas may result in drying the adhesive before tiles can be fixed causing poor adhesion.



MIXING

Place 5.0 – 5.25 liters of cold, potable water (or RAK 304-S as needed) in the mixing bucket and add slowly 25 kg bag of RAK TILE FIX-HB under continuous mixing till a uniform lump free consistency mix is achieved. For mixing process, a slow speed drill (200- 300rpm) fitted with a suitable paddle is recommended

Allow the obtained mix to stand for 3 minutes and then remix before application.

APPLICATION

Spread RAK TILE FIX-HB on the substrate to a uniform thickness using a toothed spatula, the first pass with its straight edge and the second pass immediately after, to the desired thickness using the toothed part.

FINISHING

Remove excess adhesive with damp cloth before the material has set. Joint grouting between tiles may be commenced 10 hours after tiles have been laid on the walls and 24 hours after tiles are laid on the floors.

CLEANING

Tools and equipment should be cleaned with water immediately after use. Hardened materials should be mechanically removed.

RECOMMENDATIONS

- To achieve improve adhesion strength, it is recommended to replace water with RAK BOND SBR-301



RAKAM

TECHNICAL DATA SHEET

<ul style="list-style-type: none"> • The grey type presents higher mechanical resistances. It is therefore advisable to use to fix tiles on floor • Stiffened mortar must neither be diluted with water nor with fresh mortar • Do not use RAK TILE FIX-HB on metal or non-absorbing surfaces • Do not apply RAK TILE FIX-HB in rainy weather, high winds and sand storms • Do not apply under direct sun • Keep equipment cool and use cold water • Porosity of tiles and substrates has significant effect on adhesive strength of tiles 	<p>CONSUMPTION</p> <p>Approx. 4.0 to 4.5kg RAK TILE FIX-HB per m² using notched trowel on smooth surface. Consumption will vary according to type of tiles and support condition.</p>	<p>HEALTH & SAFETY</p> <p>RAK TILE FIX-HB can be harmful to skin as it contains cement powders which may releases alkalis when mixed with water.</p> <p>During application, wear appropriate protective clothing, goggles, gloves and respiratory equipment if necessary.</p> <p>In case of contact with skin, rinse with water and again wash thoroughly with soap and water. In case of contact with eyes, rinse with plenty of water and seek medical advice accordingly.</p>								
<p>APPLICABLE STANDARDS</p> <ul style="list-style-type: none"> • EN 12004-C1T • EN 12004-C2T (if mixed with RAK BOND PVA) • ISO 13007 – C1T • ISO 13007-C2T (if mixed with RAK BOND PVA) • ANSI A 118.4 – 1992 • EN 1346 • EN 1348 	<p>STORAGE</p> <p>Store in dry covered place in the original closed bags and shelf life is 12 months if stored as recommended.</p> <p>ORDERING GUIDE</p> <table border="0"> <tr> <td>PRODUCT NO.</td> <td>102-HB</td> </tr> <tr> <td>STANDARDS</td> <td>BS-6319 / BS-1348</td> </tr> <tr> <td>PACKAGING</td> <td>20kg Plastic & 25kg Paper Bags</td> </tr> <tr> <td>COLOR</td> <td>White / Grey</td> </tr> </table>	PRODUCT NO.	102-HB	STANDARDS	BS-6319 / BS-1348	PACKAGING	20kg Plastic & 25kg Paper Bags	COLOR	White / Grey	<p>If ingested, obtain medical attention immediately. Do not induce vomiting.</p>
PRODUCT NO.	102-HB									
STANDARDS	BS-6319 / BS-1348									
PACKAGING	20kg Plastic & 25kg Paper Bags									
COLOR	White / Grey									

