

TECHNICAL DATA SHEET



RAKAM



103

RAK FLOW

Cementitious Self Levelling Compound

A cementitious self-levelling compound used for levelling of floor before applying any modern flooring system, thus avoiding any surface irregularities.

ADVANTAGES		NOTES																				
<ul style="list-style-type: none"> Self levelling and smoothing Drying time of approximately one hour Easy to use and economical Can be trowelled to obtain a smooth finish On-site addition of water Premixed to avoid site mixing errors Can be exposed to light traffic movements after 8 hours of application 	<p>application of RAK Flow All the supports should be sound, clean, free of dust, dirt, plaster, greasy matter, etc. In hot weather it is recommended to moisten the slab prior to application. New concrete should be atleast 21 days old</p>	<ul style="list-style-type: none"> Do not prepare more material that can be laid within the flow time of the product i.e-10 mins @ 35°C Do not apply in a strongly ventilated room, as the mixing water will evaporate immediately before the resin can act. Protect from direct sunlight 																				
USES	APPLICATION	POSSIBLE TOPPING																				
<p>For levelling uneven floors on:</p> <ul style="list-style-type: none"> Concrete Mortar Prefab floors, etc. 	<p>Mix the powder with clear water at a ratio of 6-7 litres of water for 25 kg of powder. Mixing can be carried out with an electric drill with spiral mixer. Mix the powder with water to obtain a lump free mixture. For better application in hot conditions, we recommend a special latex solution to mix with the powder in order to delay the setting time. The latex solution is available on request. Pour the mixed material on to the area and spread at desired thickness using a notched trowel or with similar equipment. This material is recommended for a maximum thickness of 8 mm.</p>	<p>Any glued flooring can be applied:</p> <ul style="list-style-type: none"> Bituminous Neoprene Vinyl or acrylic Resins 																				
CAUTION		SHELF LIFE																				
<p>Not recommended for external use. Not suitable for use in areas subject to standing water. Ensure that at least 75% of the tile is in contact with the adhesive.</p>		<p>Up to 12 months in unopened bags kept in suitable storage conditions away from direct sunlight and rainfall.</p>																				
TYPICAL PROPERTIES		ORDERING GUIDE																				
<table border="0"> <tr> <td>Appearance</td> <td>Grey powder</td> </tr> <tr> <td>Density</td> <td>1.51 gm/cc</td> </tr> <tr> <td>Compressive -</td> <td>1 Day: 10.5 N/mm²</td> </tr> <tr> <td>Strength @ 30oC</td> <td>28 Day : 42 N/mm²</td> </tr> <tr> <td>Light traffic</td> <td>8 hours @35°C</td> </tr> <tr> <td>Standard</td> <td>BS 8204 Pt:1</td> </tr> </table>	Appearance	Grey powder	Density	1.51 gm/cc	Compressive -	1 Day: 10.5 N/mm ²	Strength @ 30oC	28 Day : 42 N/mm ²	Light traffic	8 hours @35°C	Standard	BS 8204 Pt:1		<table border="0"> <tr> <td>PRODUCT NO.</td> <td>103</td> </tr> <tr> <td>STANDARDS</td> <td>BS : 890</td> </tr> <tr> <td>PACKAGING</td> <td>25 kg Paper / Plastic Bags</td> </tr> <tr> <td>COLOR</td> <td>Grey</td> </tr> </table>	PRODUCT NO.	103	STANDARDS	BS : 890	PACKAGING	25 kg Paper / Plastic Bags	COLOR	Grey
Appearance	Grey powder																					
Density	1.51 gm/cc																					
Compressive -	1 Day: 10.5 N/mm ²																					
Strength @ 30oC	28 Day : 42 N/mm ²																					
Light traffic	8 hours @35°C																					
Standard	BS 8204 Pt:1																					
PRODUCT NO.	103																					
STANDARDS	BS : 890																					
PACKAGING	25 kg Paper / Plastic Bags																					
COLOR	Grey																					
SURFACE PREPARATION		HEALTH AND SAFETY																				
<p>Priming The purpose of priming is to seal the substrate to prevent air release from forming bubbles and pinholes in the surface of RAK Flow The substrate should be primed using a 1:1 max of clean water and RAK Bond-PVA which should be brushed into the substrate using stiff brush and allowed to dry before</p>		<p>As with all chemical products, caution should always be exercised. Protective clothing, such as gloves and goggles, should be worn (see packaging for specific instructions). Treat any splashes to the skin or eyes with fresh water immediately. Should any of the product be accidentally swallowed, do not induce vomiting but call for medical assistance immediately. Ensure the container is available for the medical attendant to examine any relevant instructions and content details. Reseal all containers after use and ensure product is stored as instructed on the safety section of the labelling.</p>																				
COVERAGE	CURING																					
<p>2 kg/m² at a thickness of 1 mm</p>	<p>RAK Flow does not require curing; however it should be protected from direct sunlight. Air blowing over the surface of freshly laid material will dry it too fast, causing it to crack</p>																					
	CLEANING																					
	<p>Tools should be cleaned with water after use</p>																					

