



RAKAM

TECHNICAL DATA SHEET

204 RAK GROUT WP

(WATERPROOF TILE GROUT)



RAK GROUT WP is cement based, polymer modified, specially used for grouting in wet and submerged conditions.

ADVANTAGES	APPLICATION	STORAGE
<ul style="list-style-type: none"> • Non-shrinking • Chemical Resistant • Water Resistant • Non Yellowing 	<p>As a general role on a porous surface, allow 24 hours. for tiles to set prior to grouting.</p> <p>Ensure the gaps between the tiles arc clean, dry and free of adhesive.</p> <p>Mix complete 10 kg bag of powder into 2-3 litres of water with a partial slow speed drill until lump free paste is obtained.</p> <p>Apply RAK Grout-WP to the spaces between tiles. with proper rubber float or sponge, ensuring the _joints and edges are completely filled and compacted.</p> <p>Remove surplus grout with a damp cloth, wet the applied area with water after 24 hours,</p> <p>When the grout is dry, polish tiles with clean, dry and soft cloth,</p>	<p>Store in dry place below 30°C away from direct sunlight</p>
USES		<p>HEALTH AND SAFETY</p> <p>As with all chemical products, caution should always be exercised. Protective clothing, such as gloves and goggles, should be worn (see packaging for specific instructions). Treat any splashes to the skin or eyes with fresh water immediately. Should any of the product be accidentally swallowed, do not induce vomiting but call for medical assistance immediately. Ensure the container is available for the medical attendant to examine any relevant instructions and contents details. Reseal all containers after use and ensure product is stored as instructed on the safety section of the labelling.</p>
CHARACTERISTICS		<p>ORDERING GUIDE</p> <p>PRODUCT NO. 204</p> <p>STANDARDS ANSI - A118.4</p> <p>BS-5980 Class A Type1</p> <p>PACKAGING 10 kg Bags</p> <p>COLOR Standard: White / Grey</p> <p>Colors available on request</p>
<p>Working Time of Grout Paste 100 minutes at 25°C dries to tack-free film.</p> <p>Comprehensive Strength (EN-12808-3) 24 hours 6 N / mm²</p> <p>Day 28 30 N / mmi</p> <p>Flextural Strength (EN-12808-3) 28 Day 7 N 1 ma 2 impregnation</p> <p>Coverage 1 kg. of mixed product willcover 12 running meters per kg 6 mm wide x 3 mm depth.</p> <p>Water Absorption (EN-12808-5) 30 mins :< 3g 301) rains 5g</p> <p>Flammability Non flammable</p>		