# **TECHNICAL DATA SHEET**



208 RAK PROOF-FB



(Acrylic Waterproof with Fibre)

**RAK PROOF FB** is a specially formulated hi build single pack, high quality, elastomeric waterproof coating. It has outstanding durability, uv resistance and a very high degree of flexibility.

# **ADVANTAGES**

- One component; ready to apply direct from the can
- Liquid application means details are simplified and
- there are no joints in the membrane.
  Highly elastic , cures to give a permanently flexible
- resilient barrier over a wide range of tempretures. Rapid Installation; significantly reduces time spent on
- Preparatory works and detailing Excellent adhesion can be applied to a wide range of
- Substrates. Contineous adhesion prevents lateral migaration of water Impervious outstanding barrier properties ensure protection against corrosive soil conditions Thermally stable-irreversible chemical cure
- Eliminates melting and flow at high tempreture Excellent resistance to oxidation and embrittlement
- Mechanical damage to the membrane can be easily repaired by spot application

# USES

The high elasticity, excellent bond and low water permeability of RAK Proof-FB makes it ideal for a wide range of water/vapour proofing applications such as foundations, basements, tunnels, ground floors, suspended floors, car decks, roof terraces, balconies, patios, bridges, precincts, inspection pits, water retaining structures( not potable water), sewage works, inverted roofs , toilets, bathrooms, kitchens etc. The excellent chemical resistance of RAK Proof-FB makes it particularly suitable for tanking applications in areas where agressive ground water conditions prevail.

TYPICAL PROPERTIES	
Density	1.25g/cc
pH	8-8.5
Solid content	65 + 2% by weight
Elongation at -	600 %
break	
Colour	White
Toxicity	Non - toxic
Tack free time	6 hours
@30°C	
Time to full cure	48 hours at 1.3mm
@30°C	thickness
Typical cured membrane properties (at 28 days)	
Elongation	600%
(ASTM D412)	
Tensile Strength	1.8 N/mm2
(ASTM D4541)	05%
Recovery from	95%
400% elongation	
(ASTM D412) Tear resistance	16 N
(ASTM D624)	
Water vapour	6.2 g/m2/24 hrs.
transmission for 1.3 mm	0.2 y/112/24 113.
film (ASTM E96)	
Permeability @ 7 bar	NII
pressure 7th Day	
(BS EN 12390	
Part 8 : 2000)	
Artificial weathering	No loss of flexibility
, , , , , , , , , , , , , , , , , , ,	after 4000 hours
	exposure
Service tempreture	-40°C to 70°C
(contineous ambient)	
,	

# **APPLICATION**

The support must be clean, free of dust, dirt, oil, grease and loose particles. When applying on metal surfaces, remove rust and contamination for best results. Apply with brush, roller or an approximate spray. Apply a primer coat of RAK Proof-FB (80% RAK Proof-FB + 20% water) with brush, roller or spray. Once the primer coat has completely dried, apply minimum two coats of undiluted RAK Proof-FB. It is important to ensure that coat has totally cured(i.e-min 6 hours at 30°C).



#### **ORDERING GUIDE**

PRODUCT NO.	208
STANDARDS	ASTM D 4541
	BS EN 12390 Pt 8:2000
PACKAGING	5 , 20 kg Packs
COLOR	White

# SHELF LIFE

Must be protected between  $5^{\circ}$ C and  $30^{\circ}$ C. 12 months in unopened airtight containers.

#### **CLEANING**

Clean all tools with water after use.

# **HEALTH AND SAFETY**

As with all chemical products, caution should always be exercised. Protective clothing such as gloves and googles should be worn (see packaging for specific instructions). Treat any splashes to the skin or eyes with fresh water immediately. Should any of the products be accidently swallowed do not inducce vomiting, but call for medical assistance instructions and content details.Reseal all containers after use and ensure product is stored as instructed on the safety section of the labelling immediately.

AGENTS SEALAN